

ENVIRONMENTAL PRODUCT DECLARATION

as per ISO 14025 and EN 15804+A2

Owner of the Declaration	European Association for Panels and Profiles e. V. (PPA-Europe)
Publisher	Institut Bauen und Umwelt e.V. (IBU)
Programme holder	Institut Bauen und Umwelt e.V. (IBU)
Declaration number	EPD-PPA-20240127-CBG1-EN
Issue date	19/07/2024
Valid to	18/07/2029

Double skin steel faced sandwich panels with a core made of mineral wool
PPA-Europe

www.ibu-epd.com | <https://epd-online.com>



General Information

PPA-Europe

Programme holder

IBU – Institut Bauen und Umwelt e.V.
Hegelplatz 1
10117 Berlin
Germany

Declaration number

EPD-PPA-20240127-CBG1-EN

This declaration is based on the product category rules:

Double skin metal faced sandwich panels, 01/08/2021
(PCR checked and approved by the SVR)

Issue date

19/07/2024

Valid to

18/07/2029



Dipl.-Ing. Hans Peters
(Chairman of Institut Bauen und Umwelt e.V.)



Florian Pronold
(Managing Director Institut Bauen und Umwelt e.V.)

Double skin steel faced sandwich panels with a core made of mineral wool

Owner of the declaration

European Association for Panels and Profiles e. V. (PPA-Europe)
Europark Fichtenhain A 13a
47807 Krefeld
Germany

Declared product / declared unit

1 m² prefabricated double skin steel faced sandwich panels with an insulating core made of mineral wool

Scope:

This document is an association EPD for 1 m² of MW Core sandwich panel with 100 mm thickness and it represents an average EPD, based on vertical averaging of the specific producer datasets under consideration of the yearly production amounts. Its applicability is limited to continuously produced double skin steel faced sandwich panels with an insulating core made of mineral wool, which are manufactured by member companies of the European Association for Panels and Profiles.

The following member companies of the European Association for Panels and Profiles have provided data for the year 2022:

1. ArcelorMittal Group, Construction Division
 - ArcelorMittal Construction Austria
 - ArcelorMittal Construction Belgium
 - Pflaum & Söhne Bausysteme
2. Assan Panel Sanayi ve Ticaret
3. Brucha
4. Huurre Iberica
5. ISOCAB France (Kingspan Group)
6. Isolpack
7. Joris Ide Belgium (Joris Ide Group)
8. Metecno Bausysteme
9. PAGOUNI
10. Trimco.

These companies are representative for the European production of steel faced sandwich panels with mineral wool core.

This EPD comprises an annex which includes LCA results for two additional sandwich panel thicknesses: 50 mm and 200 mm. Additionally, the EPD annex contains LCA results for 1 kg steel sheet used for the panel faces and 1 m³ mineral wool (MW) used for the panel core, which allows the combination and estimation of LCA results for different panel variations.

The owner of the declaration shall be liable for the underlying information and evidence; the IBU shall not be liable with respect to manufacturer information, life cycle assessment data and evidences.

The EPD was created according to the specifications of EN 15804+A2. In the following, the standard will be simplified as *EN 15804*.

Verification

The standard EN 15804 serves as the core PCR	
Independent verification of the declaration and data according to ISO 14025:2011	
<input type="checkbox"/>	internally
<input checked="" type="checkbox"/>	externally



Mr Olivier Muller,
(Independent verifier)

Product

Product description/Product definition

The EPD applies to prefabricated double-skin steel faced sandwich panels with a core made of mineral wool, which are produced by member companies of PPA-Europe.

The profiled internal and external faces are made of a core of steel, which is protected against corrosion with zinc and organic coatings. The thermal insulating core material is made of mineral wool according to *EN 13162* with sealing tapes. The core is bonded with adhesive to the steel sheets on both sides, to ensure a certain resistance to shear forces of the panel.

The LCA is based on vertical averaging of the specific producer datasets under consideration of the respective yearly production amounts. For the placing of the product on the market in the European Union/European Free Trade Association (EU/EFTA) (with the exception of Switzerland), *CPR* applies. The product needs a Declaration of Performance taking into consideration *EN 14509* and the CE-marking. The data listed in the Declaration of Performance apply.

For the application and use, the respective national provisions apply.

Application

The products are used for self-supporting and structural applications in roof, wall and ceiling structures.

Sandwich panels in wall and roof applications take on tasks of the building physics, especially sound, heat and moisture safety. They simultaneously perform the function of air tightness of the building envelope.

Technical Data

Technical specifications for sandwich panels with a core made of mineral wool are:

- *EN 14509*
- *EN 13162*

Constructional Data

Name	Value	Unit
Density of the insulation	100 - 130	kg/m ³
Thickness of the element, when the outer layers are flat, this is the overall height of the element (D); on heavily profiled elements, this is the continuous core thickness without profile (dc)	100	mm
Thickness of the inner layer	0.5	mm
Weight	21.37	kg/m ²
Thickness of the outer layer	0.6	mm

Performance data of the product in accordance with the declaration of performance with respect to its essential characteristics according to *EN 14509*

Base materials/Ancillary materials

Composition of the sandwich panels:

Material	Thickness of the element
	100mm
Steel sheet	42%
Thermal insulation core	56%
Adhesive	2%

Steel sheet according to *EN 10346*:

S280 GD to S350 GD

Metallic coating according to *EN 10346*:

Zinc Z275, coating 275 g/m²

The zinc layer has a content of at least 99 weight percent zinc and typical thickness of 20 µm.

Organic coating according to *EN 10169*:

Polyester (SP), coil coating, 25 µm on the application side and max. 15 µm on the backside.

Thermal insulation core according to *EN 13162*:

Mineral wool

The thermal insulating core is bonded with an organic adhesive between the steel sheets.

The panels contain sealing tapes (amount on total weight < 0.1 %).

The product does not contain any SVHCs (Substances of Very High Concern) *REACH*.

Reference service life

Double-skin steel faced sandwich panels used in lightweight metal constructions must withstand a term of protection of at least 15 years. The term of protection is the period until first slight renewals in the surface are required, only if there is no need of frequent inspections and service.

The term of protection depends on the location, weather conditions and the quality of the coating.

Double-skin steel faced sandwich panels exhibit an estimated service life of 50 years depending on the use conditions.

The information in this section does not refer to a reference service life according to *ISO 15686*.

LCA: Calculation rules

Declared Unit

The declared unit is 1 m² of sandwich panel. The averaging is done based on the yearly production volume per company.

Declared unit

Name	Value	Unit
Declared unit	1	m ²
Conversion factor to 1 kg (kg/m ²)	0.047	-
Grammage of the panel (total value)	21.37	kg/m ²
Layer thickness	0,1	m

System boundary

Type of the EPD: cradle to gate - with options, module C1-C4 and module D (A1-A3, C, D and additional modules A4 and A5).

Production stage (modules A1-A3) includes processes that provide materials and energy input for the system, manufacturing and transport processes up to the factory gate, as well as waste processing.

Module A4: Delivery to the construction site with a transport distance of 100 km.

Module A5: Disposal of transport packaging at the construction site and energy for installation.

Module C1: Dismantling with the use of machinery (diesel driven).

Module C2: Transport to the site of end-of-life treatment-transport distance of 50 km .

Module C3: Metal recycling of the steel sheets.

Module C4: Disposal/landfilling of mineral wool.

Module D: Potential benefits for substitution processes or recycling materials from A5 and C3.

For the end of life, it is assumed that the steel proportion is recycled with benefits for the recycling potential declared in module D.

Geographic Representativeness

Land or region, in which the declared product system is manufactured, used or handled at the end of the product's lifespan: Europe

Comparability

Basically, a comparison or an evaluation of EPD data is only possible if all the data sets to be compared were created according to *EN 15804* and the building context, respectively the product-specific characteristics of performance, are taken into account. *LCA FE* (fka GaBi) software and databases *Sphera LCA FE* were used as calculation basis.

LCA: Scenarios and additional technical information

Characteristic product properties of biogenic carbon

Information on describing the biogenic Carbon Content at factory gate

Name	Value	Unit
Biogenic carbon content in accompanying packaging	0.13	kg C

Note: 1 kg of biogenic carbon is equivalent to 44/12 kg of CO₂

The following technical information is a basis for the declared modules.

Transport to the building site (A4)

Name	Value	Unit
Transport distance	100	km
Capacity utilisation (including empty runs)	61	%

Installation (A5)

The following packaging material is considered in A1-A3: polystyrene, polyethylene foil, cardboard and wooden pallets.

A5 covers the treatment of packaging material at the point of installation.

Installation into the building (A5)

Name	Value	Unit
Output substances following waste treatment on site	0.42	kg
Machineries for installation - diesel driven	0.233	kg/m ²

End of life (C1-C4)

Name	Value	Unit
Machineries for dismantling - diesel driven	0.233	kg/m ²
Collected separately waste type	20.69	kg
Recycling	8.59	kg
Energy recovery	-	kg
Landfilling	12.1	kg

Reuse, recovery or recycling potential (D)

Resulting potential benefits and loads for the metal recycling are declared in module D.

LCA: Results

DESCRIPTION OF THE SYSTEM BOUNDARY (X = INCLUDED IN LCA; MND = MODULE OR INDICATOR NOT DECLARED; MNR = MODULE NOT RELEVANT)

Product stage			Construction process stage		Use stage							End of life stage				Benefits and loads beyond the system boundaries
Raw material supply	Transport	Manufacturing	Transport from the gate to the site	Assembly	Use	Maintenance	Repair	Replacement	Refurbishment	Operational energy use	Operational water use	De-construction demolition	Transport	Waste processing	Disposal	Reuse-Recovery-Recycling-potential
A1	A2	A3	A4	A5	B1	B2	B3	B4	B5	B6	B7	C1	C2	C3	C4	D
X	X	X	X	X	MND	MND	MNR	MNR	MNR	MND	MND	X	X	X	X	X

RESULTS OF THE LCA - ENVIRONMENTAL IMPACT according to EN 15804+A2: 1 m² MW Sandwich panel 100 mm (21.37 kg/m²)

Parameter	Unit	A1-A3	A4	A5	C1	C2	C3	C4	D
GWP-total	kg CO ₂ eq	4.1E+01	1.55E-01	1.23E-01	8.26E-01	7.75E-02	0	1.83E-01	-1.54E+01
GWP-fossil	kg CO ₂ eq	4.03E+01	1.53E-01	7.32E-02	8.15E-01	7.65E-02	0	1.82E-01	-1.55E+01
GWP-biogenic	kg CO ₂ eq	6.94E-01	4.52E-04	4.97E-02	3.21E-03	2.26E-04	0	0	3.39E-02
GWP-luluc	kg CO ₂ eq	1.53E-02	1.42E-03	2.94E-05	7.53E-03	7.09E-04	0	5.65E-04	-7.53E-03
ODP	kg CFC11 eq	6.24E-11	1.99E-14	1.19E-13	1.06E-13	9.97E-15	0	4.62E-13	5.33E-11
AP	mol H ⁺ eq	1.77E-01	1.97E-04	1.37E-04	4.77E-03	9.83E-05	0	1.29E-03	-3.49E-02
EP-freshwater	kg P eq	3.84E-05	5.6E-07	4.71E-08	2.97E-06	2.8E-07	0	3.66E-07	-8.53E-07
EP-marine	kg N eq	2.54E-02	6.66E-05	4.26E-05	2.33E-03	3.33E-05	0	3.33E-04	-8.8E-03
EP-terrestrial	mol N eq	5.08E-01	8.02E-04	5E-04	2.58E-02	4.01E-04	0	3.66E-03	-9.76E-02
POCP	kg NMVOC eq	8.49E-02	1.69E-04	1.22E-04	6.19E-03	8.47E-05	0	1.01E-03	-2.85E-02
ADPE	kg Sb eq	6.25E-04	1.01E-08	1.18E-09	5.36E-08	5.04E-09	0	8.38E-09	7.31E-06
ADPF	MJ	4.44E+02	2.09E+00	3.68E-01	1.11E+01	1.04E+00	0	2.42E+00	-1.1E+02
WDP	m ³ world eq deprived	1.7E+00	1.85E-03	1.74E-02	9.83E-03	9.26E-04	0	2E-02	2.95E-01

GWP = Global warming potential; ODP = Depletion potential of the stratospheric ozone layer; AP = Acidification potential of land and water; EP = Eutrophication potential; POCP = Formation potential of tropospheric ozone photochemical oxidants; ADPE = Abiotic depletion potential for non-fossil resources; ADPF = Abiotic depletion potential for fossil resources; WDP = Water (user) deprivation potential

RESULTS OF THE LCA - INDICATORS TO DESCRIBE RESOURCE USE according to EN 15804+A2: 1 m² MW Sandwich panel 100 mm (21.37 kg/m²)

Parameter	Unit	A1-A3	A4	A5	C1	C2	C3	C4	D
PERE	MJ	5E+01	1.52E-01	5.3E+00	8.06E-01	7.59E-02	0	3.94E-01	2.07E+01
PERM	MJ	5.24E+00	0	-5.24E+00	0	0	0	0	0
PERT	MJ	5.53E+01	1.52E-01	6.61E-02	8.06E-01	7.59E-02	0	3.94E-01	2.07E+01
PENRE	MJ	4.29E+02	2.09E+00	4.79E+00	1.11E+01	1.05E+00	0	2.42E+00	-1.12E+02
PENRM	MJ	1.66E+01	0	-4.42E+00	0	0	0	0	0
PENRT	MJ	4.46E+02	2.09E+00	3.68E-01	1.11E+01	1.05E+00	0	2.42E+00	-1.12E+02
SM	kg	1.74E+00	0	0	0	0	0	0	0
RSF	MJ	0	0	0	0	0	0	0	0
NRSF	MJ	0	0	0	0	0	0	0	0
FW	m ³	6.98E-02	1.66E-04	4.34E-04	8.83E-04	8.32E-05	0	6.11E-04	6.74E-04

PERE = Use of renewable primary energy excluding renewable primary energy resources used as raw materials; PERM = Use of renewable primary energy resources used as raw materials; PERT = Total use of renewable primary energy resources; PENRE = Use of non-renewable primary energy excluding non-renewable primary energy resources used as raw materials; PENRM = Use of non-renewable primary energy resources used as raw materials; PENRT = Total use of non-renewable primary energy resources; SM = Use of secondary material; RSF = Use of renewable secondary fuels; NRSF = Use of non-renewable secondary fuels; FW = Use of net fresh water

RESULTS OF THE LCA - WASTE CATEGORIES AND OUTPUT FLOWS according to EN 15804+A2: 1 m² MW Sandwich panel 100 mm (21.37 kg/m²)

Parameter	Unit	A1-A3	A4	A5	C1	C2	C3	C4	D
HWD	kg	8.03E-06	6.49E-12	-7E-03	3.44E-11	3.24E-12	0	5.27E-11	-4.1E-10
NHWD	kg	6.83E+00	3.19E-04	5.58E-01	1.7E-03	1.6E-04	0	1.21E+01	-2.11E-01
RWD	kg	9.47E-03	3.92E-06	6.22E-06	2.08E-05	1.96E-06	0	2.76E-05	2.22E-03
CRU	kg	0	0	0	0	0	0	0	0
MFR	kg	3.35E-01	0	0	0	0	9.28E+00	0	0
MER	kg	0	0	0	0	0	0	0	0
EEE	MJ	0	0	1.2E-01	0	0	0	0	0
EET	MJ	0	0	2.83E-01	0	0	0	0	0

HWD = Hazardous waste disposed; NHWD = Non-hazardous waste disposed; RWD = Radioactive waste disposed; CRU = Components for re-use; MFR = Materials for recycling; MER = Materials for energy recovery; EEE = Exported electrical energy; EET = Exported thermal energy

**RESULTS OF THE LCA – additional impact categories according to EN 15804+A2-optional:
1 m² MW Sandwich panel 100 mm (21.37 kg/m²)**

Parameter	Unit	A1-A3	A4	A5	C1	C2	C3	C4	D
PM	Disease incidence	1.74E-06	1.44E-09	1.43E-09	9.51E-08	7.19E-10	0	1.59E-08	-5.13E-07
IR	kBq U235 eq	1.33E+00	5.85E-04	6.64E-04	3.1E-03	2.92E-04	0	3.19E-03	1.71E-01
ETP-fw	CTUe	1.29E+02	1.48E+00	1.51E-01	7.87E+00	7.41E-01	0	1.32E+00	-2.21E+01
HTP-c	CTUh	5.38E-08	3.03E-11	2.23E-11	1.61E-10	1.52E-11	0	2.03E-10	-2.7E-08
HTP-nc	CTUh	7.28E-07	1.61E-09	1.49E-09	1.06E-08	8.07E-10	0	2.24E-08	-6.86E-08
SQP	SQP	1.65E+02	8.72E-01	6.88E-02	4.63E+00	4.36E-01	0	5.88E-01	1.23E+01

PM = Potential incidence of disease due to PM emissions; IR = Potential Human exposure efficiency relative to U235; ETP-fw = Potential comparative Toxic Unit for ecosystems; HTP-c = Potential comparative Toxic Unit for humans (cancerogenic); HTP-nc = Potential comparative Toxic Unit for humans (not cancerogenic); SQP = Potential soil quality index

Disclaimer 1 – concerning Potential Human exposure efficiency relative to U235 (IRP) - This impact category deals mainly with the eventual impact of low-dose ionizing radiation on human health of the nuclear fuel cycle. It does not consider effects due to possible nuclear accidents, occupational exposure or radioactive waste disposal in underground facilities. Potential ionizing radiation from the soil, radon and from some construction materials is also not measured by this indicator.

Disclaimer 2 – concerning (ADP-minerals&metals, ADP-fossil, WDP, ETP-fw, HTP-c, HTP-nc, SQP) - The results of this environmental impact indicator shall be used with care as the uncertainties on these results are high as there is limited experience with the indicator.

References

EN 10169

Continuously organic coated (coil coated) steel flat products - Technical delivery conditions

EN 10346

Continuously hot-dip coated steel flat products for cold forming - Technical delivery conditions

EN 13162

Thermal insulation products for buildings - Factory made mineral wool (MW) products - Specification

EN ISO 14044

Environmental management - Life cycle assessment - Requirements and guidelines

EN 14509

Self-supporting double skin metal faced insulating panels - Factory made products - Specifications

EN 15804+A2

EN 15804+A2:2019-04: Sustainability of construction works - Environmental Product Declarations - Core rules for the product category of construction products

CPR

REGULATION (EU) No 305/2011 OF THE EUROPEAN PARLIAMENT AND OF THE COUNCIL of 9 March 2011 laying down harmonised conditions for the marketing of construction products and repealing Council Directive 89/106/EEC

LCA FE Software and Database

LCA FE software-system and CUP 2023.1 databases, University of Stuttgart and Sphera Solutions GmbH, Leinfelden-Echterdingen, 2023 (<https://sphera.com/product-sustainability-gabi-data-search/>)

PCR - Part A

Calculation rules for the Life Cycle Assessment and Requirements on the Background Report, v1.3, Institut Bauen und Umwelt e.V., www.bau-umwelt.com, August 2021

PCR - Part B

Double skin metal faced sandwich panels, Institut Bauen und Umwelt e.V., www.bau-umwelt.com, v8., October 2023

REACH

Regulation (EC) No 1907/2006 of the European Parliament and of the Council of 18 December 2006 concerning the Registration, Evaluation, Authorisation and Restriction of Chemicals



ArcelorMittal





Publisher

Institut Bauen und Umwelt e.V.
Hegelplatz 1
10117 Berlin
Germany

+49 (0)30 3087748- 0
info@ibu-epd.com
www.ibu-epd.com



Programme holder

Institut Bauen und Umwelt e.V.
Hegelplatz 1
10117 Berlin
Germany

+49 (0)30 3087748- 0
info@ibu-epd.com
www.ibu-epd.com



Author of the Life Cycle Assessment

Sphera Solutions GmbH
Hauptstraße 111- 113
70771 Leinfelden-Echterdingen
Germany

+49 (0)711 341817-0
info@sphera.com
www.sphera.com



Owner of the Declaration

European Association for Panels and Profiles e. V.
(PPA-Europe)
Europark Fichtenhain A 13a
47807 Krefeld
Germany

+49 2151 93630-0
info@ppa-europe.eu
www.ppa-europe.eu